



ASTM A333 Low Temperature Pipe

ASTM A333 (ASME S/A-333) Pipe grades permit low temperature service. ASTM A333 Pipe shall be made by the seamless or welding process with the addition of no filler metal in the welding operation.

Sunny Steel Supply supplies a full range of ASTM A333 (ASME S/A 333)

Scope of ASTM A333

ASTM A333 covers nominal (average) wall seamless and welded carbon and alloy steel pipe intended for use at low temperatures. Several grades of ferritic steel are included. Some product sizes may not be available under this specification because heavier wall thicknesses have an adverse effect on low-temperature impact properties.

Material & Manufacture

ASTM A333 pipe shall be made by the seamless or welding process with the addition of no filler metal in the welding operation.

Heat Treatment Requirements

All seamless and welded pipe shall be treated to control their microstructure by the following methods: Normalizing per A 333/A 333M-05 section 4.2.1.1; section 4.2.1.2 or section 4.2.1.3 Quenched and Tempered per A 333/A 333M - 05 section 4.2.2.1 Double Normalized and Tempered per A 333/A 333M -

Tensile Requirements

The material shall conform to the requirements as proscribed:

	Grade 1		Grade 3		Grade 6	
	psi	MPa	psi	MPa	psi	MPa
Tensile Strength, min	55,000	380	65,000	450	60,000	415
Yield Strength, min	30,000	205	35,000	240	35,000	240
Longitudinal Transverse Longitudinal Transverse Longitudinal Transverse						
Elongation in 2 in. or 50 mm, (or 4D), min, %:						
Basic minimum elongation for walls 5/16 in. [8 mm] and over in thickness, strip tests, and for all small sizes tested in full section	35	35	30	20	30	16.5
When the standard round 2-in. or 50-mm gage length or proportionally smaller size test specimen with the gage length equal to 4D (4 times the diameter) is used	28	20	22	14	22	12
For strip tests, a deduction for each 1/32in. [0.8 mm] decrease in wall thickness below 5/16 in. [8 mm] from the basic minimum elongation of the following percentage	1.75	1.25	1.50	1.00	1.50	1.00
Elongation in 2 in. or 50 mm, min, %:						

Impact Requirements

For Grades 1, 3 and 6, the notched-bar impact properties of each set of three impact specimens, including specimens for the welded joint in welded pipe with wall thicknesses of 0.120 in. [3 mm] and larger, shall not be less than the values prescribed:

Size of Specimen, min	Minimum Average Notched Bar Impact Value of Each Set of Three Specimens		Minimum Notched Bar Impact Value of One Specimen Only of a Set		Impact Temperature	
	ft-lbf	J	ft-lbf	J	Grade	Min Impact Test Temp
10 by 10	13	18	10	14		F C
10 by 7.5	10	14	8	11	1	-50 -45
10 by 6.67	9	12	7	9	3	-150 -100
10 by 5	7	9	5	7	6	-50 -45
10 by 3.33	5	7	3	4		
10 by 2.5	4	5	3	4		

Mechanical Testing

Transverse or Longitudinal Tension Test and Flattening Test, Hardness Test, or Bend Test For material heat treated in a batch-type furnace, tests shall be made on 5% of the pipe from each treated lot. For small lots, at least one pipe shall be tested. For material heat treated by the continuous process, tests shall be made on a sufficient number of pipe to constitute 5% of the lot, but in no case less than 2 pipe. Hydrostatic Test Impact Test One notched bar impact test, consisting of breaking three specimens shall be made from each heat represented in a heat-treatment load on specimens taken from the finished pipe.




Lengths

Lengths required shall be specified on order. If no definite lengths required, following practice applies:
Single Random -- 17' ~ 24' lengths Double Random -- 36' ~ 44' lengths









Size tolerance

Wall Thickness		Grade 1		Grade 3		Grade 6	
in.	mm	Longitudinal	Transverse	Longitudinal	Transverse	Longitudinal	Transverse
5/16 (0.312)	8	35	25	30	20	30	16
9/32 (.281)	7.2	33	24	28	19	28	15
1/4 (.250)	6.4	32	23	27	18	27	15
7/32 (.219)	5.6	30		26		26	
3/16 (.188)	4.8	28		24		24	
5/32 (.156)	4	26		22		22	
1/8 (.125)	3.2	25		21		21	
3/32 (.094)	2.4	23		20		20	
1/16 (.063)	1.6	21		18		18	

Chemical Requirements of ASTM A333 Grade1, 3, 6

Element	Composition, %		
	Grade 1	Grade 3	Grade 6
Carbon, max	0.30	0.19	0.30
Manganese	0.40 - 1.06	0.31 - 0.64	0.29 - 1.06
Phosphorous, max	0.025	0.025	0.025
Sulfur, max	0.025	0.025	0.025
Silicon		0.18 - 0.37	0.10 min
Nickel		3.18 - 3.82	

For each reduction of 0.01% carbon below 0.30%, an increase of 0.05% manganese above 1.06% would be permitted to a maximum of 1.35% manganese. When Grade 6 is ordered under this specification, supplying an alloy grade that specifically requires the addition of any element other than those listed for the ordered grade is not permitted. However, the addition of elements required for the DE oxidation of the steel is permitted.

Referenced Documents

ASTM A 370 Test Methods and Definitions for Mechanical testing of Steel Products ASTM A999/A 999M Specification for General requirements for Alloy and Stainless Steel Pipe.

ASTM A 671 Specification for General requirements for Alloy and Stainless Steel Pipe ASTM E 23 Test Methods for Notched bar Impact testing of Metallic Materials

Get in Touch

If you are interested in our products or cooperating with us, even having a comment or a suggestion please contact us now, for more detailed information.

Tel.: +8621 3378 0199 | E-mail: sales@sunnysteel.com

----- www.sunnysteel.com -----

